

# ADVANCENE™ EE-1801-AAB

Linear Low Density Polyethylene Resin

## Overview

ADVANCENE™ EE-1801-AAB is a part of an LLDPE series offering excellent drawdown and puncture resistance combined with high gloss and clarity. They are also frequently used as a blend partner with LDPE resins to improve film properties and processability. Several additive packages are available according to the required surface properties.

## Applications

- Agricultural Film.
- Bag in Box.
- Barrier Food Packaging.
- Blown Film.
- Bread Bags.
- Food Packaging.
- Form Fill and Seal Packaging.
- Freezer Film.
- Garment Film.
- General Packaging.
- Heavy Duty Bags.
- Ice Bags.
- Industrial Liners.
- Industrial Packaging.
- Lamination Film.
- Liners.
- Multilayer Packaging Film.
- Packaging Films.
- Produce Bags.
- Refuse Bags.
- Shoppers.
- Stand Up Pouches.
- Trash Bags.

Physical	Typical Value (SI)	Test Based On
Density	0.918 g/cm <sup>3</sup>	ASTM D792
Melt Index (190°C/2.16 kg)	1.0 g/10min	ASTM D1238, ISO 1133
Peak Melting Temperature	120 °C	ASTM D3418, ISO 3146
Films Properties	Typical Value (SI)	Test Based On
Tensile Strength at Break MD	57.0 MPa	ASTM D882
Tensile Strength at Break TD	38.0 MPa	ASTM D882
Elongation at Break MD	590%	ASTM D882
Elongation at Break TD	860%	ASTM D882
Secant Modulus MD - 1% Secant	220 MPa	ASTM D882
Secant Modulus TD - 1% Secant	250 MPa	ASTM D882
Dart Drop Impact	120 g	ASTM D1709A, ISO 7765
Elmendorf Tear Strength MD	120 g	ASTM D1922, ISO 6383-2
Elmendorf Tear Strength TD	480 g	ASTM D1922, ISO 6383-2
Optical Properties	Typical Value (SI)	Test Based On
Gloss (45°)	47	ASTM D2457
Haze	9.0%	ASTM D1003

## Processing Statement

The film properties have been measured on 30 µm (1.18 mil) thick films (Blow-up ratio : 2.5)

## Notes :

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

### AVAILABILITY

This product is supplied in 25 kg bags in secured pallets of 60 bags (1.500 MT net). It is also supplied in jumbo bags of 1000 kg capacity.

### STORAGE

The product should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage can be found in Safety Information Sheet for this product.

### SAFETY

The product is not classified as a hazardous mixture.

Dust and fines from the product carry a risk of dust explosion. All equipment should be properly earthed. Inhalation of dust should be avoided as it may cause irritation of the respiratory system. Small amounts of fumes are generated during processing of the product. Proper ventilation is therefore required.

A Safety Information Sheet is available on request. Please contact your ETHYDCO representative for more details on various aspects of safety, recovery and disposal of the product.

### RECYCLING

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

### RELATED DOCUMENT

Most datasheets and statements are available on ETHYDCO website [www.ethydco-eg.com](http://www.ethydco-eg.com). If more information is required, please contact a ETHYDCO representative for information.

### DISCLAIMER

**The product(s) mentioned herein are not intended to be used for medical, pharmaceutical applications and we do not support their use for such applications.**

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

**ETHYDCO makes no warranties which extend beyond the description contained herein. Nothing herein constitute any warranty of merchantability or fitness for a particular purpose.**

**It is the customer's responsibility to inspect and test our products in order to satisfy itself suitability of the products for the customer's particular purpose. The customer is responsible appropriate, safe and legal use, processing and handling of our products.**

No liability can be accepted in respect of the use of ETHYDCO products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

ADVANCENE™ is a trademark of ETHYDCO